

Amendments to th Claims

The claims have been amended as follows. Underlines indicate insertions and ~~strikeouts~~ indicate deletions.

Claims 1-8 (Cancelled).

B¹
~~9.~~ (Currently amended) A low selectivity deposition method comprising:
forming a first part of a nucleation layer on a first surface of a substrate;
forming a second part of a nucleation layer on a second surface of the substrate;
and

forming a deposition layer comprising a chemisorbed first specie layer about one monolayer thick on the first and second parts of the nucleation layer substantially non-selectively on the first part of the nucleation layer compared to the second part, even though the first and second surfaces of the substrate exhibit a property of the deposition layer forming less readily on the first surface compared to the second surface.

B²
2
~~10.~~ (Original) The deposition method of claim ~~9~~ wherein the forming the first and the second part of the nucleation layer occurs by chemical vapor deposition.

B²
3
11. (Original) The deposition method of claim ~~9~~ wherein the forming the first and the second part of the nucleation layer occurs by atomic layer deposition.

⁴
~~12~~. (Original) The deposition method of claim ³~~11~~ wherein the atomic layer deposition comprises contacting the substrate with only one precursor specie at a time.

⁵
~~13~~. (Original) The deposition method of claim ¹~~8~~ wherein the forming the first and the second part of the nucleation layer occurs simultaneously.

⁶
~~14~~. (Original) The deposition method of claim ¹~~8~~ wherein the forming the first and the second part of the nucleation layer occurs simultaneously and the nucleation layer forms substantially non-selectively on the first surface of the substrate compared to the second surface.

⁷
~~15~~. (Original) The deposition method of claim ¹~~8~~ wherein the forming the deposition layer is performed in situ of the forming the first and the second part of the nucleation layer.

⁸
~~16~~. (Original) The deposition method of claim ¹~~8~~ wherein the second part of the nucleation layer comprises a plurality of components also comprised by the first part.

⁹
~~17~~. (Original) The deposition method of claim ¹~~8~~ wherein the first and the second parts of the nucleation layer comprise silicon nitride, aluminum oxide, or tantalum oxide.

¹⁰
~~18~~. (Original) The deposition method of claim ~~9~~¹ wherein the first and the second parts of the nucleation layer consist essentially of same components in approximately same proportions.

¹¹
~~19~~. (Original) The deposition method of claim ~~9~~¹ wherein a composition of the first part of the nucleation layer differs from a composition of the second part of the nucleation layer.

¹²
~~20~~. (Original) The deposition method of claim ~~9~~¹ wherein the first and the second parts of the nucleation layer comprise silicon nitride and the first part further comprises oxygen.

12
Cont.

¹³
~~21~~. (Original) The deposition method of claim ~~9~~¹ wherein a thickness of the nucleation layer comprises less than about 20 Angstroms.

¹⁴
~~22~~. (Original) The deposition method of claim ~~21~~¹³ wherein the thickness comprises less than about 6 Angstroms.

¹⁵
~~23~~. (Original) The deposition method of claim ~~9~~¹ wherein a thickness of the first part of the nucleation layer is greater than 50% of a thickness of the second part.

¹⁶
~~24~~. (Original) The deposition method of claim ~~23~~¹⁵ wherein the thickness of the first part is greater than 80% of the thickness of the second part.

32

✓

¹¹
~~25~~. (Currently amended) The deposition method of claim ~~9~~¹ wherein the deposition layer ~~comprises a~~ chemisorbed first specie at least layer is one monolayer thick.

¹⁸
~~26~~. (Currently amended) The deposition method of claim ~~25~~¹ wherein the first surface of the substrate exhibits a property of chemisorbing the first specie at a slower rate compared to the second surface.

¹⁹
~~27~~. (Currently amended) The deposition method of claim ~~25~~¹ wherein the forming the deposition layer further ~~comprising~~ comprises forming a layer at least one monolayer thick of a chemisorbed second specie different from the first specie on the first specie layer.

²⁰
~~28~~. (Currently amended) The deposition method of claim ~~27~~¹⁹ wherein the first and second specie layers ~~each~~ layer consists essentially of a monolayer.

²¹
~~29~~. (Original) The deposition method of claim ~~27~~¹⁹ wherein the first and second specie layers, in combination, comprise silicon and nitrogen.

²²
~~30~~. (Original) The deposition method of claim ~~27~~¹⁹ wherein the nucleation layer comprises a material also comprised by the first and second specie layers combined.

23
31. (Currently amended) A low selectivity deposition method comprising:

simultaneously forming a first part of a nucleation layer on an insulative oxide material and a second part of the nucleation layer on a semiconductive material; and contacting the nucleation layer with an initiation precursor and forming an initiation layer at least about one monolayer thick on the first and second parts of the nucleation layer substantially non-selectively on the first part of the nucleation layer compared to the second part.

24
32. (Currently amended) The deposition method of claim 23 wherein the initiation layer ~~consists essentially of a~~ is one monolayer thick.

25
33. (Original) The deposition method of claim 23 wherein the first and the second parts of the nucleation layer consist essentially of same components in approximately same proportions.

26
34. (Original) The deposition method of claim 23 wherein the first and the second parts of the nucleation layer comprise silicon nitride and the first part further comprises oxygen.

27
35. (Original) The deposition method of claim 23 wherein a thickness of the nucleation layer comprises less than about 20 Angstroms.

²⁸
~~36~~. (Original) The deposition method of claim ~~31~~²³ wherein a thickness of the first part of the nucleation layer is greater than about 50% of a thickness of the second part.

²⁹
~~37~~. (Original) The deposition method of claim ~~31~~²³ wherein the insulative oxide exhibits a property of chemisorbing the initiation precursor at a slower rate compared to the semiconductive material.

³⁰
~~38~~. (Original) The deposition method of claim ~~31~~²³ further comprising contacting the initiation layer with at least one deposition precursor and forming a deposition layer at least one monolayer thick on the initiation layer.

³¹
~~39~~. (Original) The deposition method of claim ~~38~~³⁰ wherein the deposition layer consists essentially of a monolayer.

³²
~~40~~. (Original) The deposition method of claim ~~38~~³⁰ wherein the deposition precursor consists essentially of a single precursor specie.

³³
~~41~~. (Original) The deposition method of claim ~~38~~³⁰ wherein the initiation and deposition layers, in combination, comprise silicon and nitrogen, or tantalum and oxygen, or aluminum and oxygen.

[Claims 42-46 (Cancelled).

³⁷~~47~~. (Currently amended) A low selectivity deposition method comprising:

atomic layer depositing a nucleation substance chemisorbed on a first surface and a second surface of a substrate substantially non-selectively, wherein the first surface exhibits a property of chemisorbing an atomic layer deposition precursor at a slower rate compared to the second surface and the nucleation substance exhibits a property of chemisorbing the precursor at an approximately equal rate over the first surface compared to over the second surface.

³⁵~~48~~. (Original) The deposition method of claim ³⁴~~47~~ wherein the nucleation substance comprises an approximately homogeneous composition over the first and the second surface.

³⁶~~49~~. (Original) The deposition method of claim ³⁴~~47~~ wherein the nucleation layer comprises silicon nitride and a nucleation layer part that is over the first surface further comprises oxygen.

³⁷~~50~~. (Original) The deposition method of claim ³⁴~~47~~ wherein a thickness of the nucleation layer comprises less than about 20 Angstroms.

³⁸~~51~~. (Original) The deposition method of claim ³⁴~~47~~ wherein a thickness of a nucleation layer part that is over the first surface is greater than 50% of a thickness a nucleation layer part that is over the second surface.

39 52. (Currently amended) A low selectivity deposition method comprising:
placing a substrate in a deposition chamber;

forming a first part of a nucleation layer on a first surface of the substrate in the chamber;

29
forming a second part of a nucleation layer on a second surface of the substrate in the chamber; and

without removing the substrate from the chamber, forming a layer at least about one monolayer thick of a first chemisorbed precursor on the first and second parts of the nucleation layer substantially non-selectively on the first part of the nucleation layer compared to the second part.

40 53. (Original) The deposition method of claim 39 wherein the forming the first and the second part of the nucleation layer occurs simultaneously and the nucleation layer forms substantially non-selectively on the first surface of the substrate compared to the second surface.

41 54. (Original) The deposition method of claim 39 wherein the first surface of the substrate exhibits a property of chemisorbing the first precursor at a slower rate compared to the second surface.

42 55. (Original) The deposition method of claim 39 wherein the first surface comprises borophosphosilicate glass and the second surface comprises polysilicon.

43
56.

(Original) A low selectivity deposition method comprising:
placing a substrate in a first chamber;
forming a first part of a nucleation layer on a first surface of the substrate in the first chamber;
forming a second part of a nucleation layer on a second surface of the substrate in the first chamber;
removing the substrate from the first chamber and placing it in a second chamber different from the first; and
forming a layer of a first chemisorbed specie at least one monolayer thick on the first and second parts of the nucleation layer in the second chamber substantially non-selectively on the first part of the nucleation layer compared to the second part.

210
Wm.

44

57. (Original) The deposition method of claim ⁴³~~56~~ wherein the forming the first and the second part of the nucleation layer occurs simultaneously and the nucleation layer forms substantially non-selectively on the first surface of the substrate compared to the second surface.

45
58.

(Original) The deposition method of claim ⁴³~~56~~ wherein the first surface of the substrate exhibits a property of chemisorbing the first specie at a slower rate compared to the second surface.

46

⁴³~~58~~. (Original) The deposition method of claim ⁴³~~56~~ wherein the first surface comprises borophosphosilicate glass and the second surface comprises polysilicon.